



IfBB

Institute for Bioplastics
and Biocomposites



Technical datasheet

IfBB Blend HD115x-black

Product description

The bio-based IfBB Blend HD115x-black is a specially developed PLA modification with a natural residue as a dye, which is processed via injection moulding at a mould temperature of 100 °C. The high mould temperature, in combination with the material composition, offers the advantage of optimised cycle times and thermomechanical properties.

Physical properties

Mechanical properties	Value	Unit	Test method / Norm
Tensile modulus of elasticity	~ 3600	MPa	DIN EN ISO 527-2
Tensile strength	~ 35	MPa	DIN EN ISO 527-2
Charpy impact strength	~ 10	kJ/m ²	DIN EN ISO 179 / 1 e U (23°C)
Thermal properties	Value	Unit	Test method / Norm
Heat deflection temperature (HDT-B)	> 115	°C	DIN EN ISO 75-2
Melting point	~ 165	°C	DIN EN ISO 11357-1
Rheological properties	Value	Unit	Test method / Norm
Melt flow rate (190°C / 2.16kg)	> 2	g/10min	DIN EN ISO 1133
Melt volume rate (190°C / 2.16kg)	> 2.5	cm ³ /10min	DIN EN ISO 1133
Other properties	Value	Unit	Test method / Norm
Density	~ 1.27	g/cm ³	DIN 1183-1, A

This technical datasheet is intended to provide information and advice. All values are guidelines. No liability may be derived therefrom.

Processing via injection moulding

Material conditioning	Value	Unit
Processing humidity	< 250	ppm
Drying temperature	60 - 100	°C
Drying duration	6 - 12	h
Injection moulding settings	Value	Unit
Mould temperature*	25	°C
Temperature zones		
Flange	60	°C
Zone 1	170	°C
Zone 2	170	°C
Zone 3	185	°C
Zone 4	210	°C
Zone 11	250	°C

*The thermomechanical properties are dependent on the mould temperature; the specified temperature should therefore be used. Furthermore, at this temperature, the shortest residual cooling time/cycle time is to be expected.

Contact

Hanover University of Applied Sciences and Arts
IfBB – Institute for Bioplastics and Biocomposites
Faculty II – Mechanical and Bioprocess Engineering
Heisterbergallee 10A
30453 Hanover

Tel.: 0511 / 9296 - 2268

Fax: 0511 / 9296 - 99 2268

E-Mail: info@ifbb-hannover.de

Internet: <http://www.ifbb-hannover.de>

This technical datasheet is intended to provide information and advice. All values are guidelines. No liability may be derived therefrom.